

PAYA RESIN CO

KIND	PROPERTY							USES								
	SOLID	VISCOSITY(C P)	PH	TG(°C)	PLASTICIZER	EMOLSFIRE		TEXTILE	BUILDING	PAINT	WOOD	PAPER	CERAMIC	PRIMER	SHOE	BINDER
STYRENE BUTADIENE LATEX																
PAYTEX-NL 25	45-46	80-250	9-10	-25	0	A	برای اولین بار در ایران	●								
PAYTEX-NL15	46-47	80-200	8-9	-15	0	A		●		●		●				
PAYTEX-NL 05	46-47	50-110	8-9	-5	0	A		●	●					●		●
PAYTEX-M 100	48-49	60-150	7.5-8.5	0	0	A		●				●				
PAYTEX-M 05	48-49	60-150	7.5-8.5	5	0	A		●				●		●		
PAYTEX-M15	49-50	70-120	7.5-8.5	15	0	A				●						
PAYTEX-PH 25	50-51	80-350	7-8	25	0	A		●								
PAYTEX-PH 48	49-51	60-100	7-8	48	0	A		●								
PAYTEX-PH 87	50-51	50-100	6.5-7.5	87	0	A		●							●	
POLY VINYL ACETATE HOMOPOLYMERS																
H-21	49-51	110000-150000	4-5	24	0	N		●		●	●					
H-21A	49-51	90000-130000	4-5	23	0	N		●								
H-521	50-52	340000-410000	4-5	25	1	N		●	●							
PHP-24	49-51	320000-390000	4-4.5	30	0	N		●								
H-77	49-51	170000-230000	4-4.5	31	0	N		●								
COPOLYMER(VINYL ACETATE,VEOVA,ACRYLIC ESTERS)																
HCO-625	51-53	3800-4500	4-4.5	14	0	A			●	●			●			
HCO-631	50-51	2100-2900	4-4.5	14	0	A			●	●						
ACRYLIC - STYRENIC COPOLYMERS																
PAYACRYIL-115	50-51	21500-22500	7-8	15	0	A		●		●						
PAYACRYIL-120	50-51	3800-4800	7-8	20	0	A		●		●						
PAYACRYIL-141	50-51	21500-22500	7-8	41	0	A			●	●					●	
ADHESIVE																
H-101	42	48000-58000	4.3	15	2	N					●	●				
H-110	49-50	1900-2700	4.3	15	8	N						●				
ST-32(STIFFENER)	17	30000-35000	7-8	32	0	A-N		●				●				

We can change the specification of our product, according our customers application.

Tel: 0098-355-5373703

Web: www.abnil.com

Fax: 0098-335-5374304

Email: office@abnil.com

must be stored in 5-40 °C and under cover to avoid rain, frost and sunlight.